



SPECIFICATION SHEET
Trans-X Mineral Oil

<u>TYPE OF TEST</u>	<u>ASTM METHOD</u>	<u>LIMIT VALUES</u>
Color	D-1500	0.5 Maximum
Visual Examination	D-1524	Bright & Clear
Dielectric Breakdown, kV	D-877	30 Minimum
Water Content, ppm	D-1533	25 Maximum
Interfacial Tension, dynes/cm,	D-971	40 Minimum
Neutralization Number, mg	D-974	0.015 Maximum
Power Factor, 25°C	D-924	
@ 25° C		0.05 Maximum
@ 100° C		0.5 Maximum
Specific Gravity, 60/60	D 1298	0.91 Maximum
Oxidation Inhibitor (DBPC)	D-2668	
Type I Oil (Uninhibited):		0.08 maximum 0.00 minimum
Type II Oil (Inhibited):		0.30 maximum 0.15 minimum
Corrosive Sulfur:	D-1275	Non-Corrosive
Polychlorinated Biphenyls	EPA 8082	< 1 ppm